

GP Batteries

Product Specifications

Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 1 of 7

Specifications for GN24A 1.5V LR03 AAA size

Alkaline Battery

Revision History

Revision No.	Justification	Issue Date
0	New released	Oct 27, 2009
1	Revised Section 6 & 7 note 1	Sep 14, 2011.

GP Batteries

Product Specifications

Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 2 of 7

1. APPLICABILITY

This specification is applicable to GP Super Alkaline Cell, GN24A(No mercury added).

2. GENERAL

- 2.1 Type designation : LR03 (IEC/JIS), 24A (ANSI)
- 2.2 Nominal voltage : 1.5V
- 2.3 Shape and dimension : Refer to Drawing 1.
- 2.4 Typical weight : 11.5g
- 2.5 Warranty period : 36 months
- 2.6 Jacket : Foil jacket

3. APPEARANCE

There shall be no dirt, scratch or deformation detrimental to practical service in appearance.

4. CELL VOLTAGE

4.1 Test method

- Method of sampling : MIL-STD-105E level II single sampling normal inspection.
- Voltmeter : Digital Voltmeter (DVM) with the precision of 1mV (internal resistance not less than 1 Megohm)
- Test temperature : 20±2°C

4.2 Off Load Voltage

At shipping	12 months after manufactured
1.50-1.65V	1.50-1.65V

4.3 On Load Voltage

Initial	12 months after manufactured
Above 1.40V	Above 1.37V

Load resistance : 3.9ohm ± 0.5% (measure time : 0.3 seconds)

GP Batteries

Product Specifications

Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 3 of 7

5. SERVICE OUTPUT

5.1 Test method

- (1) The resistance of external discharge circuit shall be as specified plus or minus 0.5%.
- (2) The duration of discharge time periods shall be as specified plus or minus 1%.
- (3) Storage shall be at $20\pm 2^{\circ}\text{C}$, $65\pm 20\%\text{RH}$ and discharge tests shall be at $20\pm 2^{\circ}\text{C}$, $65\pm 20\%\text{RH}$.

5.2 Service Life

	Test Mode	Application	Standard	Initial (Nominal)	Initial (Minimum)	12 months storage at 20°C (Nominal)
Service life at $20\pm 2^{\circ}\text{C}$	5.1 Ω 4M/H, 8H/D (EPV=0.9V)	Portable lighting	IEC/ANSI	220M	190M	190M
	10 Ω 1H/D (EPV=0.9V)	Tape recorders	IEC/ANSI	480M	420M	400M
	75 Ω 4H/D (EPV=0.9V)	Transistor radios	IEC	71H	67H	69H
	600mA 10s on 50s off 1H/D (EPV=0.9V)	Photo Flash	IEC/ANSI	280cycles	220cycles	250cycles
	20 Ω 24H/D (EPV=0.9V)	Reference test		18.3H	17.2H	17.0H

s: second M: minute H: hour D: day EPV: end point voltage

*The initial discharge test shall commence within 30 days of manufacture. During this period, the cells shall be stored under room temperature conditions.
($20\pm 2^{\circ}\text{C}$ and $65\pm 20\%$ relative humidity)

5.3 Operating temperature: -20°C to 54°C ($65\pm 20\%\text{RH}$)

5.4 Storage temperature: -30°C to 30°C ($65\pm 20\%\text{RH}$)

GP Batteries

Product Specifications

Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 4 of 7

6. ELECTROLYTE LEAKAGE

	Test Items	Test Conditions	Requirements
6.1	Arrival at warehouse	Within two months after shipping	There shall be no leakage observed with naked eye and no bulging or deformation of batteries in excess of dimensions on shown in the Drawing 1
6.2	Long term storage	After storing for 12 months at $20 \pm 15^{\circ}\text{C}$, $65 \pm 20\% \text{RH}$	
6.3	High Temperature	Test specimens shall be kept standing at $45 \pm 2^{\circ}\text{C}$ and below 70% RH or less for 30days	
6.4	Over-discharge	20 Ohm continuously discharge down to 0.6V at $20 \pm 2^{\circ}\text{C}$, $65 \pm 20\% \text{RH}$	

7. QUALITY ASSURANCE

DESCRIPTION	SAMPLING PLAN
Battery dimensions	0.65% (Note 5)
Appearance	1.0% (Note 5)
Off load voltage	0.65% (Note 5)
On load voltage	1.0% (Note 5)
Service output	Note 1 (Note 5)
Leakage 6.1	0.65% (Note 2 & 5)
6.2	Note 3
6.3	Note 4
6.4	Note 4

Note 1 : Acceptance / rejection in accordance with IEC publication 60086-1 (2011), Sub-clause 5.3.

- 1) Test nine batteries.
- 2) Calculate the average without the exclusion of any result.
- 3) If this average is equal to or greater than the specified figure and no more than one battery has a service output of less than 80% of the specified figure, the batteries are considered to conform for service output.
- 4) If this average is less than the specified figure and/or more than one battery has a service output of less than 80% of the specified figure, repeat the test on another sample of nine batteries and calculate the average as previously.
- 5) If the average of this second test is equal to or greater than the specified figure and no more than one battery has a service output of less than 80% of the specified figure, the batteries are considered to conform for service output.
- 6) If the average of second test is less than the specified figure and/or more than one battery has a service output of less than 80% of the specified figure, the batteries are considered not to conform and no further testing is permitted.

Note 2: Leakage on arrival at warehouse is within two months after shipping.

Note 3: Sample size : $n=20$, Judgement : $A_c=1$ $R_e=2$

Note 4: Sample size : $n=20$, Judgement : $A_c=0$, $R_e=1$

Note 5: AQL General Inspection level II, single sampling plan.

GP Batteries

Product Specifications


Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 5 of 7

8. NORMAL PACKAGING (REFERENCE ONLY)



*Special packaging shall be a form agreed by both parties.

GP Batteries

Product Specifications

Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 6 of 7

Precaution & Handling

1. Do not attempt to take batteries apart or subject them to pressure or impact. Heat may be generated or fire may result. The alkaline electrolyte is harmful to eyes and skin, and it may damage clothing upon contact.
2. Keep away from children. If swallowed, contact a physician at once.
3. Do not mix GP batteries with other battery brands or batteries of a different chemistry such as alkaline and zinc carbon.
4. Do not short circuit batteries, permanent damage to batteries may result.
5. Do not incinerate or mutilate batteries, may burst or release toxic material.
6. Do not solder directly to cells or batteries.
7. Store batteries in a cool dry place.
8. If find any noise, excessive temperature or leakage from a battery, please stop its use.
9. When not using a battery, disconnect it from the device.
10. Do not mix new batteries in use with semi-used batteries.
11. When find battery power down during use, please switch off the device and take batteries out.
12. Never put a battery into water or seawater.
13. Do not recharge batteries.

Storage

1. Store in a cool, dry place before use.
2. Do not keep batteries at temperature of 30°C or above.
3. Do not keep batteries at relative humidity of 75% or above.

GP Batteries

Product Specifications


Model No.:GN24A

Document Number: GNA004N

Revision:01

Page 7 of 7

Drawing 1



Unit: mm